

PRÆPARATUM E  
STANNO.

PREPARATION OF TIN.

---

STANNUM PULVERATUM.

POWDERED TIN.

TAKE of Tin six pounds.

Melt it in an iron vessel, and stir it with an iron rod, until a powder floats on the surface. Take off the powder, and, when cold, pass it through a sieve.

R E M A R K.

This powder of Tin is slightly calcined. Like that made by granulation, and the *Limatura Stanni*, it is intended as an anthelmintic; and given to children from ten grains to a scruple;—to adults, from one dram to two or more.

PRÆPARATA

P R Æ P A R A T A E  
Z I N C O .

PREPARATIONS OF ZINC.

---

ZINCUM CALCINATUM.

CALCINED ZINC.

**T**AKE of Zinc, broken into small pieces,  
eight ounces.

Cast the pieces of Zinc, at several times,  
into an ignited, large, and deep, crucible,  
placed leaning, or half-upright, putting  
upon it another crucible in such a manner  
that the air may have free access to the  
burning Zinc.

Take out the Calx as soon as it appears,  
and sift its white and lighter part.