

PRÆPARATUM E  
STANNO.

PREPARATION OF TIN.

---

STANNUM PULVERATUM.

POWDERED TIN.

**T**AKE of Tin six pounds.

Melt in an iron vessel, and stir it with an iron rod untill a powder floats on the surface. Take off the powder, and, when cold, pass it through a sieve.

R E M A R K.

This powder of Tin is slightly calcined. Like that made by granulation, and the *Limatura Stanni*, it is intended as an anthelmintic, and given to children from ten grains to a scruple; — to adults, from one dram to two or more.

N

PRÆPA-